



LOCTITE[®] 5905[™]

February 2006

PRODUCT DESCRIPTION

LOCTITE[®] 5905[™] provides the following product characteristics:

Technology	Silicone
Chemical Type	Oxime silicone
Appearance (uncured)	Black paste ^{LMS}
Components	One component - requires no mixing
Viscosity	Thixotropic paste
Cure	Moisture cure, Room temperature vulcanizing (RTV)
Application	Gasketing, Sealing or Bonding
Specific Benefit	Non-corrosive, Nonslumping

LOCTITE[®] 5905[™] is designed primarily as a form in place (FIP) gasket or sealant to seal devices. It may be suitable for select cure in place (CIP) applications. It has an excellent bead height profile, is easy to dispense and has good resistance to most engine fluids. Typical applications include rigid and flexible flange type covers made of either metal or plastic, timing covers, oil sumps and oil filled gauge type sight glass covers. LOCTITE[®] 5905[™] may not be suitable for applications involving long term contact with ethylene glycol. The thixotropic nature of LOCTITE[®] 5905[™] reduces the migration of liquid product after application to the substrate.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.2 to 1.4 ^{LMS}
Flash Point - See MSDS	
Flow, ISO 7390, mm:	
After 2 minutes	≤0.5 ^{LMS}
Extrusion Rate, g/min:	
Pressure 0.62 MPa, temperature 25 °C:	
Semco Cartridge	200 to 380 ^{LMS}

TYPICAL CURING PERFORMANCE


Skin Over Time

Skin over time is the time the surface of the adhesive forms a skin upon exposure to atmospheric moisture at 25 ± 2 °C, 50 ± 5% RH.

Skin Over Time, minutes	12 to 30 ^{LMS}
-------------------------	-------------------------

Cure Speed

The graph below shows shear strength developed with time on grit blasted mild steel lapshears at a bond gap of 1.0 mm. Cure condition 23±2 °C, 50±5% RH. Strength is determined according to ISO 4587.



TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 7 days @ 25 °C / 50±5 % RH

Physical Properties:

Shore Hardness, ISO 868, Durometer A	39
Elongation, ISO 37, %	≥250 ^{LMS}
Tensile Strength, ISO 37	N/mm ² ≥1.6 ^{LMS} (psi) (≥230)
Tensile Modulus, ISO 37	N/mm ² 2.66 (psi) (385)

TYPICAL PERFORMANCE OF CURED MATERIAL

Adhesive Properties

Cured for 7 days @ 25 °C / 50±5 % RH, 1 mm gap

Lap Shear Strength, ISO 4587:

Mild steel	N/mm ² 0.94 (psi) (135)
Glass	N/mm ² 1.03 (psi) (150)
Polycarbonate	N/mm ² 0.95 (psi) (135)
Aluminum (Alclad)	N/mm ² ≥1.0 ^{LMS} (psi) (≥145)
Aluminum (Alclad) to Mild steel	N/mm ² 0.97 (psi) (140)
Aluminum (Alclad) to Glass	N/mm ² 0.99 (psi) (145)
Aluminum (Alclad) to Polycarbonate	N/mm ² 1.23 (psi) (180)

Heat Aging

Aged @ 125 °C for 168 hours

Lap Shear Strength, ISO 4587:

Aluminum to Glass	N/mm ² 1.65 (psi) (240)
Aluminum to Polycarbonate	N/mm ² 1.54 (psi) (225)

Aged @ 200 °C for 168 hours

Lap Shear Strength, ISO 4587:

Aluminum to Aluminum (Alclad)	N/mm ²	1.54
	(psi)	(220)

Immersion

Aged @ 125 °C for 168 hours

5W30 oil:

Lap Shear Strength, ISO 4587:

Aluminum to Glass	N/mm ²	0.88
	(psi)	(130)
Aluminum to Polycarbonate	N/mm ²	0.75
	(psi)	(110)

ASTM 902 oil:

Lap Shear Strength, ISO 4587:

Aluminum to Glass	N/mm ²	0.94
	(psi)	(135)
Aluminum to Polycarbonate	N/mm ²	1.08
	(psi)	(155)

Aged @ 150 °C for 168 hours

5W30 oil:

Lap Shear Strength, ISO 4587:

Aluminum to Aluminum (Alclad)	N/mm ²	0.77
	(psi)	(110)

ASTM 902 oil:

Lap Shear Strength, ISO 4587:

Aluminum to Aluminum (Alclad)	N/mm ²	0.6
	(psi)	(85)

TYPICAL ENVIRONMENTAL RESISTANCE

Cured for 7 days @ 25 °C / 50±5 % RH

Heat Aging

Aged @ 200 °C for 168 hours:

Change in Durometer, Points (Initial =)	4
Change in Tensile Strength, %	14
Change in Elongation, %	-41

Typical Fluid Immersion Properties

Aged @ 150 °C for 168 hours:

5W30 oil:

Change in Durometer, Points (Initial =)	-18
Change in Tensile Strength, %	-24
Change in Elongation, %	-24
Volume Swell, %	25

ASTM IRM 902 oil:

Change in Durometer, Points (Initial =)	-15
Change in Tensile Strength, %	6
Change in Elongation, %	46
Volume Swell, %	8

Aged @ 125 °C for 168 hours:

Ethylene glycol/water, 50:50:

Change in Durometer, Points (Initial =)	-26
Change in Tensile Strength, %	-76
Change in Elongation, %	152
Volume Swell, %	2

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Directions for use

1. LOCTITE® 5905™ should be applied as a bead to clean surface.
2. To function as a cured in place gasket it should be allowed to cure prior to assembly.
3. If utilized as a formed in place gasket it should be assembled within 15 minutes for optimum results.
4. Excess material can be easily wiped away with non-polar solvents.

Loctite Material Specification^{LMS}

LMS dated November 8, 2005. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties. Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 2.0